

SPECIFICATIONS

A clean, contemporary sawn stone paired with an exotic, natural sparkling gray color.

THIN VENEER

LENGTH	4" - 30" Random
HEIGHT*	Sawn 2 ¼", 5", & 7 ¾"
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft ²

*Typical height ratio: 20% = 2 ¼", 50% = 5", 30% = 7 ¾". Additional heights available upon request

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.14%
BULK SPECIFIC GRAVITY	2.78

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	22,230 psi
PARALLEL TO RIFT, WET	14,610 psi
PERPENDICULAR TO RIFT, DRY	23,510 psi
PERPENDICULAR TO RIFT, WET	14,040 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,040 psi
PARALLEL TO RIFT, WET	1,700 psi
PERPENDICULAR TO RIFT, DRY	4,070 psi
PERPENDICULAR TO RIFT, WET	1,700 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	1,640 psi
PARALLEL TO RIFT, WET	1,260 psi
PERPENDICULAR TO RIFT, DRY	2,840 psi
PERPENDICULAR TO RIFT, WET	2,440 psi

