

SPECIFICATIONS

A natural glistening split face in warm burgundy, desert tones with the occasional copper hue.

THIN VENEER

LENGTH	4" - 30" Random
HEIGHT	2" - 9" Random
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft ²

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.12%
BULK SPECIFIC GRAVITY	2.65

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	26,530 psi
PARALLEL TO RIFT, WET	26,460 psi
PERPENDICULAR TO RIFT, DRY	20,450 psi
PERPENDICULAR TO RIFT, WET	11,600 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,020 psi
PARALLEL TO RIFT, WET	1,550 psi
PERPENDICULAR TO RIFT, DRY	2,140 psi
PERPENDICULAR TO RIFT, WET	1,700 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	2,390 psi
PARALLEL TO RIFT, WET	2,270 psi
PERPENDICULAR TO RIFT, DRY	2,450 psi
PERPENDICULAR TO RIFT, WET	1,950 psi

