

GALAXY GLITTER DIMENSIONAL DRYSTACK

SPECIFICATIONS

Exotic sparkling natural stone sawn to a contemporary, linear style with little to no joint exposed.

THIN VENEER

LENGTH	4" - 30" Random
HEIGHT*	Sawn 2", 4", & 6"
THICKNESS	3/4" - 1 1/2"
YIELD	10-15 lbs/ft ²

*Typical height ratio: 20% = 2", 50% = 4", 30% = 6". Additional heights available upon request.

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.14%
BULK SPECIFIC GRAVITY	2.78

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	22,230 psi
PARALLEL TO RIFT, WET	14,610 psi
PERPENDICULAR TO RIFT, DRY	23,510 psi
PERPENDICULAR TO RIFT, WET	14,040 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,040 psi
PARALLEL TO RIFT, WET	1,700 psi
PERPENDICULAR TO RIFT, DRY	4,070 psi
PERPENDICULAR TO RIFT, WET	1,700 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	1,640 psi
PARALLEL TO RIFT, WET	1,260 psi
PERPENDICULAR TO RIFT, DRY	2,840 psi
PERPENDICULAR TO RIFT, WET	2,440 psi

