

EBONY GLITTER DIMENSIONAL DRYSTACK

SPECIFICATIONS

A rich black quartzite with a subtle mica fleck in a contemporary, linear style with little to no joint exposed.

THIN VENEER

LENGTH	4" - 30" Random (12" Average)
HEIGHT*	Sawn 2", 4", & 6"
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft ²

*Typical height ratio: 20% = 2", 50% = 4", 30% = 6". Additional heights available upon request

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.12%
BULK SPECIFIC GRAVITY	2.782

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	19,870 psi
PARALLEL TO RIFT, WET	8,452 psi
PERPENDICULAR TO RIFT, DRY	19,013 psi
PERPENDICULAR TO RIFT, WET	8,088 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,086 psi
PARALLEL TO RIFT, WET	1,173 psi
PERPENDICULAR TO RIFT, DRY	1,584 psi
PERPENDICULAR TO RIFT, WET	1,142 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	1,341 psi
PARALLEL TO RIFT, WET	1,053 psi
PERPENDICULAR TO RIFT, DRY	1,883 psi
PERPENDICULAR TO RIFT, WET	1,395 psi

