

## SPECIFICATIONS

A clean, contemporary sawn stone paired with an exotic, natural sparkling gray color.

### THIN VENEER

LENGTH	4" - 30" Random (12" Average)
HEIGHT*	Sawn 2 1/4", 5", & 7 3/4"
THICKNESS	3/4" - 1 1/2"
YIELD	10-15 lbs/ft <sup>2</sup>

\*Typical height ratio: 20% = 2 3/4", 50% = 5", 30% = 7 3/4". Additional heights available upon request

## ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.14%
BULK SPECIFIC GRAVITY	2.78

## ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	22,230 psi
PARALLEL TO RIFT, WET	14,610 psi
PERPENDICULAR TO RIFT, DRY	23,510 psi
PERPENDICULAR TO RIFT, WET	14,040 psi

## ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,040 psi
PARALLEL TO RIFT, WET	1,700 psi
PERPENDICULAR TO RIFT, DRY	4,070 psi
PERPENDICULAR TO RIFT, WET	1,700 psi

## ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	1,640 psi
PARALLEL TO RIFT, WET	1,260 psi
PERPENDICULAR TO RIFT, DRY	2,840 psi
PERPENDICULAR TO RIFT, WET	2,440 psi

