

HARVEST GOLD SANDSTONE DIMENSIONAL

SPECIFICATIONS

A warm range of cream to gold neutrals sawn to a contemporary, linear style.

THIN VENEER

LENGTH	4" - 30" Random (12" Average)
HEIGHT*	Sawn 2 ¼", 5", & 7 ¾"
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft ²

*Typical height ratio: 20% = 2 ¼", 50% = 5", 30% = 7 ¾". Additional heights available upon request

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.78%
BULK SPECIFIC GRAVITY	2.489

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	31,890 psi
PARALLEL TO RIFT, WET	20,950 psi
PERPENDICULAR TO RIFT, DRY	30,860 psi
PERPENDICULAR TO RIFT, WET	29,970 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,000 psi
PARALLEL TO RIFT, WET	1,980 psi
PERPENDICULAR TO RIFT, DRY	1,910 psi
PERPENDICULAR TO RIFT, WET	1,520 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	2,160 psi
PARALLEL TO RIFT, WET	1,820 psi
PERPENDICULAR TO RIFT, DRY	1,760 psi
PERPENDICULAR TO RIFT, WET	1,690 psi

