

SPECIFICATIONS

A radiant and sparkling burgundy rose quartzite in an elegant castle cut.

THIN VENEER

| | |
|-----------|-------------------------------|
| LENGTH | 4" - 24" Random (12" Average) |
| HEIGHT | 4" - 12" Random |
| THICKNESS | ¾" - 1 ½" |
| YIELD | 10-15 lbs/ft² |

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

| | |
|-----------------------|------|
| WATER ABSORPTION | .12% |
| BULK SPECIFIC GRAVITY | 2.65 |

ASTM C-170 – COMPRESSIVE STRENGTH

| | |
|----------------------------|------------|
| PARALLEL TO RIFT DRY | 26,530 psi |
| PARALLEL TO RIFT, WET | 26,460 psi |
| PERPENDICULAR TO RIFT, DRY | 20,450 psi |
| PERPENDICULAR TO RIFT, WET | 11,600 psi |

ASTM C-99 – MODULUS OF RUPTURE

| | |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY | 2,020 psi |
| PARALLEL TO RIFT, WET | 1,550 psi |
| PERPENDICULAR TO RIFT, DRY | 2,140 psi |
| PERPENDICULAR TO RIFT, WET | 1,700 psi |

ASTM C-880 – FLEXURAL STRENGTH

| | |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY | 2,390 psi |
| PARALLEL TO RIFT, WET | 2,270 psi |
| PERPENDICULAR TO RIFT, DRY | 2,450 psi |
| PERPENDICULAR TO RIFT, WET | 1,950 psi |

