




American Engineering Testing, Inc.
 Wausau | Green Bay
 4203 Schofield Ave, Ste 1 | 3194 Market St., Ste C
 Schofield, WI 54476 | Green Bay, WI 54304
 (715)359-3534 | (920)347-1286
 Toll Free: (800)972-6364
 www.amengtest.com

Material Test Report

Report No: MAT:12-02155-W3-S1
Issue No: 1

Client: KAFKA GRANITE, LLC **CC:** John Meyer
Project: 12-02155
 2016 CONSTRUCTION PROJECTS

This document shall not be reproduced, except in full, without written approval from American Engineering Testing, Inc.

Date of Issue: 3/21/2016
Reviewed By: Paul Michlig, CET
 Construction Manager

Sample Details

Sample ID 12-02155-W3-S1
Field Sample ID 1
Date Sampled 3/14/2016
Source Kafka Granite
Material Caramel 3/8" - 1/4"
Specification None
Sampling Method Sampled by Client
Location Kafka Granite
Date Submitted 3/15/2016

Test Results

Description	Method	Result	Limits
Specific Gravity (OD)	ASTM C 127 - 2012	2.45	
Specific Gravity (SSD)		2.50	
Apparent Specific Gravity		2.58	
Absorption (%)		2.0	
Density Determined Without First Drying?		No	
Additional Notes			
Date Tested		3/16/2016	

Comments

N/A

April 12, 2017

Mr. Jeremy Bores
Kafka Granite, LLC
550 East Highway 153
Mosinee, WI 54455

Re: Mohs Hardness Testing
2017 Construction Projects
Schofield, WI
AET Project No. 12-02541

Mr. Bores:

This report presents the results of our Mohs hardness testing of one sample of stone submitted by you on April 5, 2017. The stone is to be referred to as "Caramel Quartzite". Nine stones were submitted to our laboratory and one was chosen for testing. The scope of our work in this report was confined to performing Mohs hardness testing on one stone sample.

Conclusions

Based on our observations and analysis our opinions are as follows:

1. The overall hardness of the "Caramel Quartzite" stone is approximately 7.5 on the Mohs scale. The number is based upon testing values of the overall hardness of the rock using Mohs hardness picks.
2. The stone appeared to generally consist of a fine grained metamorphic rock. A hardness value determination of the stone based upon the mineral assemblage was not conducted. Mohs picks with hardness 3 through 8 were used on the stone. The Mohs hardness picks determined an approximate overall hardness of 7.5. This hardness is a more consistent result than using the mineral assemblage because the Mohs hardness picks were drawn directly across a freshly lapped surface of the stone.
3. In general, rocks are not homogeneous with regards to Mohs mineral hardness. The best effort was made to accomplish the hardness analysis at a representative area within the stone selected. Because rocks can consist of several different minerals with different quantities and different hardness, and the Mohs scale represents the hardness of individual minerals, the Mohs scale should only be used as an approximation when determining the overall hardness of a rock.

Mr. Jeremy Bores
Sample ID: Caramel Quartzite
AET Project No. 12-02541
April 12, 2017
Page 2 of 2

Procedures

Our work was performed on April 6, 2017 and subsequent dates. The hardness testing was completed through the use of standard geologic Mohs hardness points and optical microscopy on a lapped hand sample. The review was performed in general accordance with Standard Operating Procedure 24-LAB-004, "Petrographic Examination of Aggregates for Concrete, ASTM C295." Observations were made using an Olympus SZX-12 stereo-zoom binocular microscope with magnification up to 160x.

Photographs are included to illustrate our work and conclusions.

Remarks

The sample will be retained for a period of at least sixty days from the date of this report. Unless further instructions are received by that time, the sample may be discarded. The geologic services for this project have been conducted in a manner consistent with that level of care and skill exercised by members of the profession currently practicing in this area under similar budget and time constraints. The results relate only to the sample analyzed. No warranty, express or implied, is made.

It has been a pleasure to serve you on this project. Should you have any questions on this report, please do not hesitate to call.

Respectfully,


American Engineering Testing, Inc.



Christopher J. Braaten, PG, CPG
Petrographer/Geologist
MN License #48312
Phone: 651-659-1352
cbraaten@amengtest.com

Reviewed by:

American Engineering Testing, Inc.



Gerard Moulzolf, PG
Vice President/Principal Petrographer
MN License #30023
Phone: 651-659-1346
gmoulzolf@amengtest.com

PHOTO: 1



SAMPLE ID: Caramel Quartzite DESCRIPTION: Overall view of the sample as received.

PHOTO: 2



SAMPLE ID: Caramel Quartzite DESCRIPTION: View of the stone selected for hardness testing.

PHOTO: 3



SAMPLE ID:
MAG:

Caramel Quartzite
5x

DESCRIPTION: View of the lapped cross section of the stone.

PHOTO: 4



SAMPLE ID:
MAG:

Caramel Quartzite
5x

DESCRIPTION: View of the lapped cross section of the stone after Mohs hardness testing. Note that hardness picks 3 through 7 did not scratch and hardness pick 8 scratched all minerals. The general Mohs hardness would be approximately 7.5.