



AMERICAN HERITAGE GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	124	6.2	93.8	80-100%
#8	516	25.7	68.1	65-90%
#16	444	22.1	46	40-60%
#30	248	12.3	33.7	25-55%
#50	166	8.2	25.5	15-35%
#100	154	7.7	17.8	10-20%
#200	144	7.2	10.6	7-15%
Pan	214	10.6	0.0	
TOTAL	2010			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	124	6.2	93.8	80-100%
#8	516	25.7	68.1	55-90%
#16	444	22.1	46	40-60%
#30	248	12.3	33.7	25-55%
#50	166	8.2	25.5	15-35%
#100	154	7.7	17.8	10-20%
#200	144	7.2	10.6	5-15%
Pan	214	10.6	0.0	
TOTAL	2010			