



ANTIQUE ROSE MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	138	6.9	93.2	80-100%
#8	420	20.9	72.3	65-90%
#16	594	29.6	42.7	40-60%
#30	308	15.3	27.4	25-55%
#50	200	10	17.4	15-35%
#100	92	4.6	12.8	10-20%
#200	80	4	8.8	7-15%
Pan	176	8.8	0.0	
TOTAL	2008			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	138	6.9	93.2	80-100%
#8	420	20.9	72.3	55-90%
#16	594	29.6	42.7	40-60%
#30	308	15.3	27.4	25-55%
#50	200	10	17.4	15-35%
#100	92	4.6	12.8	10-20%
#200	80	4	8.8	5-15%
Pan	176	8.8	0.0	
TOTAL	2008			