



AUTUMN BLEND MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	10.1	89.7	80-100%
#8	150	14.3	75.4	65-90%
#16	222	21.2	54.2	40-60%
#30	220	21	33.2	25-55%
#50	134	12.8	20.4	15-35%
#100	80	7.6	12.8	10-20%
#200	48	4.6	8.2	7-15%
Pan	86	8.2	0.0	
TOTAL	1046			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	10.1	89.7	80-100%
#8	150	14.3	75.4	55-90%
#16	222	21.2	54.2	40-60%
#30	220	21	33.2	25-55%
#50	134	12.8	20.4	15-35%
#100	80	7.6	12.8	10-20%
#200	48	4.6	8.2	5-15%
Pan	86	8.2	0.0	
TOTAL	1046			