



BEIGE BLEND MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	86	4.3	95.7	80-100%
#8	416	20.8	74.9	65-90%
#16	376	18.8	56.1	40-60%
#30	278	13.9	42.2	25-55%
#50	246	12.3	29.9	15-35%
#100	220	11	18.9	10-20%
#200	202	10.1	8.8	7-15%
Pan	176	8.8	0.0	
TOTAL	2000			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	86	4.3	95.7	80-100%
#8	416	20.8	74.9	55-90%
#16	376	18.8	56.1	40-60%
#30	278	13.9	42.2	25-55%
#50	246	12.3	29.9	15-35%
#100	220	11	18.9	10-20%
#200	202	10.1	8.8	5-15%
Pan	176	8.8	0.0	
TOTAL	2000			