



BLACK DIAMOND GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	5.3	94.0	80-100%
#8	478	25.3	68.7	65-90%
#16	414	21.9	46.8	40-60%
#30	138	7.3	39.5	25-55%
#50	164	8.7	30.8	15-35%
#100	248	12.4	18.4	10-20%
#200	160	8.4	10.0	7-15%
Pan	188	10.0	0.0	
TOTAL	1886			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	5.3	94.0	80-100%
#8	478	25.3	68.7	55-90%
#16	414	21.9	46.8	40-60%
#30	138	7.3	39.5	25-55%
#50	164	8.7	30.8	15-35%
#100	248	12.4	18.4	10-20%
#200	160	8.4	10.0	5-15%
Pan	188	10.0	0.0	
TOTAL	1886			