



BLUE MAHOGANY GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	5.6	94.5	80-100%
#8	380	20.2	74.3	65-90%
#16	320	17	57.3	40-60%
#30	280	14.9	42.4	25-55%
#50	286	15.2	27.2	15-35%
#100	164	8.7	18.5	10-20%
#200	126	6.7	11.8	7-15%
Pan	222	11.7	0.0	
TOTAL	1884			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	106	5.6	94.5	80-100%
#8	380	20.2	74.3	55-90%
#16	320	17	57.3	40-60%
#30	280	14.9	42.4	25-55%
#50	286	15.2	27.2	15-35%
#100	164	8.7	18.5	10-20%
#200	126	6.7	11.8	5-15%
Pan	222	11.7	0.0	
TOTAL	1884			