



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	104	4.1	96.0	80-100%
#8	694	27.2	68.8	65-90%
#16	548	21.5	47.3	40-60%
#30	352	13.8	33.5	25-55%
#50	244	9.6	23.9	15-35%
#100	244	9.6	14.3	10-20%
#200	178	7.0	7.3	7-15%
Pan	186	7.3	0.0	
TOTAL	2550			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	104	4.1	96.0	80-100%
#8	694	27.2	68.8	55-90%
#16	548	21.5	47.3	40-60%
#30	352	13.8	33.5	25-55%
#50	244	9.6	23.9	15-35%
#100	244	9.6	14.3	10-20%
#200	178	7.0	7.3	5-15%
Pan	186	7.3	0.0	
TOTAL	2550			