



BURNT SIENNA MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	136	6.8	93.2	80-100%
#8	480	24.0	69.2	65-90%
#16	456	22.8	46.4	40-60%
#30	274	13.7	32.7	25-55%
#50	176	8.8	23.9	15-35%
#100	146	7.3	16.6	10-20%
#200	152	7.6	9.0	7-15%
Pan	180	9.0	0.0	
TOTAL	2000			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	136	6.8	93.2	80-100%
#8	480	24.0	69.2	55-90%
#16	456	22.8	46.4	40-60%
#30	274	13.7	32.7	25-55%
#50	176	8.8	23.9	15-35%
#100	146	7.3	16.6	10-20%
#200	152	7.6	9.0	5-15%
Pan	180	9.0	0.0	
TOTAL	2000			