



CHERRY CREEK GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	224	11.2	88.3	80-100%
#8	226	11.3	77.0	65-90%
#16	386	19.3	57.7	40-60%
#30	274	13.7	44.0	25-55%
#50	328	16.4	27.6	15-35%
#100	180	9.0	18.6	10-20%
#200	164	8.2	10.4	7-15%
Pan	208	10.4	0.0	
TOTAL	1990			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	224	11.2	88.3	80-100%
#8	226	11.3	77.0	55-90%
#16	386	19.3	57.7	40-60%
#30	274	13.7	44.0	25-55%
#50	328	16.4	27.6	15-35%
#100	180	9.0	18.6	10-20%
#200	164	8.2	10.4	5-15%
Pan	208	10.4	0.0	
TOTAL	1990			