



**DYNAMITE ORANGE GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	290	23.2	76.8	65-90%
#16	298	23.8	53.0	40-60%
#30	210	16.8	36.2	25-55%
#50	142	11.4	24.8	15-35%
#100	96	7.7	17.1	10-20%
#200	76	6.1	11.0	7-15%
Pan	138	11.0	0.0	
<b>TOTAL</b>	1250			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	290	23.2	76.8	55-90%
#16	298	23.8	53.0	40-60%
#30	210	16.8	36.2	25-55%
#50	142	11.4	24.8	15-35%
#100	96	7.7	17.1	10-20%
#200	76	6.1	11.0	5-15%
Pan	138	11.0	0.0	
<b>TOTAL</b>	1250			