



**EVERGREEN GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	134	8.2	91.8	80-100%
#8	350	21.6	70.3	65-90%
#16	296	18.2	52.1	40-60%
#30	226	13.9	38.2	25-55%
#50	182	11.2	27.0	15-35%
#100	130	8.0	19.0	10-20%
#200	160	9.8	9.2	7-15%
Pan	150	9.2	0.0	
<b>TOTAL</b>	1628			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	134	8.2	91.8	80-100%
#8	350	21.6	70.3	55-90%
#16	296	18.2	52.1	40-60%
#30	226	13.9	38.2	25-55%
#50	182	11.2	27.0	15-35%
#100	130	8.0	19.0	10-20%
#200	160	9.8	9.2	5-15%
Pan	150	9.2	0.0	
<b>TOTAL</b>	1628			