

GUN METAL MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	530	33.0	67.1	65-90%
#16	286	17.8	49.3	40-60%
#30	246	15.3	34.0	25-55%
#50	164	10.2	23.8	15-35%
#100	88	5.5	18.3	10-20%
#200	66	4.1	14.2	7-15%
Pan	228	14.2	0.0	
TOTAL	1608			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	530	33.0	67.1	55-90%
#16	286	17.8	49.3	40-60%
#30	246	15.3	34.0	25-55%
#50	164	10.2	23.8	15-35%
#100	88	5.5	18.3	10-20%
#200	66	4.1	14.2	5-15%
Pan	228	14.2	0.0	
TOTAL	1608			