

## SPECIFICATIONS

A range of cool and gray earth tones with an irregular boulder look.

### THIN VENEER

|           |                    |
|-----------|--------------------|
| LENGTH    | 6" - 16" Irregular |
| HEIGHT    | 6" - 16" Irregular |
| THICKNESS | ¾" - 1 ½"          |
| YIELD     | 10-15 lbs/ft²      |

### ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

|                       |       |
|-----------------------|-------|
| WATER ABSORPTION      | .03%  |
| BULK SPECIFIC GRAVITY | 2.823 |

### ASTM C-170 – COMPRESSIVE STRENGTH

|                            |            |
|----------------------------|------------|
| PARALLEL TO RIFT DRY       | 22,500 psi |
| PARALLEL TO RIFT, WET      | 24,370 psi |
| PERPENDICULAR TO RIFT, DRY | 31,720 psi |
| PERPENDICULAR TO RIFT, WET | 30,430 psi |

### ASTM C-99 – MODULUS OF RUPTURE

|                            |           |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY       | 1,040 psi |
| PARALLEL TO RIFT, WET      | 1,600 psi |
| PERPENDICULAR TO RIFT, DRY | 1,660 psi |
| PERPENDICULAR TO RIFT, WET | 1,450 psi |

### ASTM C-880 – FLEXURAL STRENGTH

|                            |           |
|----------------------------|-----------|
| PARALLEL TO RIFT DRY       | 2,160 psi |
| PARALLEL TO RIFT, WET      | 1,560 psi |
| PERPENDICULAR TO RIFT, DRY | 3,830 psi |
| PERPENDICULAR TO RIFT, WET | 3,000 psi |

