

SPECIFICATIONS

A natural seam face marble with a vibrant range of earth tones.

THIN VENEER

LENGTH	4" - 30" Random (10" Average)
HEIGHT	2" - 9" Random
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft²

ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.03%
BULK SPECIFIC GRAVITY	2.823

ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	22,500 psi
PARALLEL TO RIFT, WET	24,370 psi
PERPENDICULAR TO RIFT, DRY	31,720 psi
PERPENDICULAR TO RIFT, WET	30,430 psi

ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	1,040 psi
PARALLEL TO RIFT, WET	1,600 psi
PERPENDICULAR TO RIFT, DRY	1,660 psi
PERPENDICULAR TO RIFT, WET	1,450 psi

ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	2,160 psi
PARALLEL TO RIFT, WET	1,560 psi
PERPENDICULAR TO RIFT, DRY	3,830 psi
PERPENDICULAR TO RIFT, WET	3,000 psi

