

# HARVEST GOLD SANDSTONE LEDGESTONE

## SPECIFICATIONS

A warm range of cream to gold neutrals in a low-height drystack.

### THIN VENEER

LENGTH	4" - 16" Random (6" Average)
HEIGHT*	1" - 3" Sawn Random
THICKNESS	¾" - 1 ½"
YIELD	10-15 lbs/ft <sup>2</sup>

### ASTM C-97 – ABSORPTION & BULK SPECIFIC GRAVITY

WATER ABSORPTION	.78%
BULK SPECIFIC GRAVITY	2.489

### ASTM C-170 – COMPRESSIVE STRENGTH

PARALLEL TO RIFT DRY	31,890 psi
PARALLEL TO RIFT, WET	20,950 psi
PERPENDICULAR TO RIFT, DRY	30,860 psi
PERPENDICULAR TO RIFT, WET	29,970 psi

### ASTM C-99 – MODULUS OF RUPTURE

PARALLEL TO RIFT DRY	2,000 psi
PARALLEL TO RIFT, WET	1,980 psi
PERPENDICULAR TO RIFT, DRY	1,910 psi
PERPENDICULAR TO RIFT, WET	1,520 psi

### ASTM C-880 – FLEXURAL STRENGTH

PARALLEL TO RIFT DRY	2,160 psi
PARALLEL TO RIFT, WET	1,820 psi
PERPENDICULAR TO RIFT, DRY	1,760 psi
PERPENDICULAR TO RIFT, WET	1,690 psi

