



**IMPERIAL GRAY GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	336	20.7	79.1	65-90%
#16	340	21.1	58.0	40-60%
#30	290	18.0	40.0	25-55%
#50	212	13.2	26.8	15-35%
#100	146	9.1	17.7	10-20%
#200	110	6.8	10.9	7-15%
Pan	176	10.9	0.0	
<b>TOTAL</b>	1610			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	336	20.7	79.1	55-90%
#16	340	21.1	58.0	40-60%
#30	290	18.0	40.0	25-55%
#50	212	13.2	26.8	15-35%
#100	146	9.1	17.7	10-20%
#200	110	6.8	10.9	5-15%
Pan	176	10.9	0.0	
<b>TOTAL</b>	1610			