



**MAUVE GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	42	2.2	97.7	80-100%
#8	436	23.4	74.3	65-90%
#16	424	22.7	51.6	40-60%
#30	274	14.7	36.9	25-55%
#50	214	11.5	25.4	15-35%
#100	148	7.9	17.5	10-20%
#200	122	6.5	11.0	7-15%
Pan	206	11.0	0.0	
<b>TOTAL</b>	1866			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	42	2.2	97.7	80-100%
#8	436	23.4	74.3	55-90%
#16	424	22.7	51.6	40-60%
#30	274	14.7	36.9	25-55%
#50	214	11.5	25.4	15-35%
#100	148	7.9	17.5	10-20%
#200	122	6.5	11.0	5-15%
Pan	206	11.0	0.0	
<b>TOTAL</b>	1866			