



MIDNIGHT BLUE GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	74	3.5	96.4	80-100%
#8	476	22.5	73.9	65-90%
#16	418	19.8	54.1	40-60%
#30	448	21.2	32.9	25-55%
#50	286	13.5	19.4	15-35%
#100	168	7.9	11.5	10-20%
#200	94	4.4	7.1	7-15%
Pan	150	7.1	0.0	
TOTAL	2114			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	74	3.5	96.4	80-100%
#8	476	22.5	73.9	55-90%
#16	418	19.8	54.1	40-60%
#30	448	21.2	32.9	25-55%
#50	286	13.5	19.4	15-35%
#100	168	7.9	11.5	10-20%
#200	94	4.4	7.1	5-15%
Pan	150	7.1	0.0	
TOTAL	2114			