



MISTY GRAY MARBLE
PATHWAY SIEVE ANALYSIS



| STANDARD PATHWAY SIEVE ANALYSIS | | | | |
|---------------------------------|-------|------------|-----------|--------------|
| SIEVE | GRAMS | % RETAINED | % PASSING | SPEC PASSING |
| 3/8" | 0 | 0.0 | 100 | 100% |
| #4 | 120 | 4.9 | 95.2 | 80-100% |
| #8 | 460 | 18.7 | 76.5 | 65-90% |
| #16 | 476 | 19.3 | 57.2 | 40-60% |
| #30 | 384 | 15.6 | 41.6 | 25-55% |
| #50 | 292 | 11.9 | 29.7 | 15-35% |
| #100 | 312 | 12.7 | 17.0 | 10-20% |
| #200 | 204 | 8.3 | 8.7 | 7-15% |
| Pan | 214 | 8.7 | 0.0 | |
| TOTAL | 2462 | | | |

| STABILIZED PATHWAY SIEVE ANALYSIS | | | | |
|-----------------------------------|-------|------------|-----------|--------------|
| SIEVE | GRAMS | % RETAINED | % PASSING | SPEC PASSING |
| 3/8" | 0 | 0.0 | 100 | 100% |
| #4 | 120 | 4.9 | 95.2 | 80-100% |
| #8 | 460 | 18.7 | 76.5 | 55-90% |
| #16 | 476 | 19.3 | 57.2 | 40-60% |
| #30 | 384 | 15.6 | 41.6 | 25-55% |
| #50 | 292 | 11.9 | 29.7 | 15-35% |
| #100 | 312 | 12.7 | 17.0 | 10-20% |
| #200 | 204 | 8.3 | 8.7 | 5-15% |
| Pan | 214 | 8.7 | 0.0 | |
| TOTAL | 2462 | | | |