



**PLATINUM GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	180	8.8	91.2	80-100%
#8	512	25.1	66.1	65-90%
#16	296	14.5	51.6	40-60%
#30	302	14.8	36.8	25-55%
#50	238	11.6	25.2	15-35%
#100	156	7.6	17.6	10-20%
#200	128	6.3	11.3	7-15%
Pan	230	11.3	0.0	
<b>TOTAL</b>	2042			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	180	8.8	91.2	80-100%
#8	512	25.1	66.1	55-90%
#16	296	14.5	51.6	40-60%
#30	302	14.8	36.8	25-55%
#50	238	11.6	25.2	15-35%
#100	156	7.6	17.6	10-20%
#200	128	6.3	11.3	5-15%
Pan	230	11.3	0.0	
<b>TOTAL</b>	2042			