



**POLAR WHITE MARBLE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	186	6.3	93.6	80-100%
#8	782	26.3	67.3	65-90%
#16	524	17.6	49.7	40-60%
#30	444	14.9	34.8	25-55%
#50	376	12.6	22.2	15-35%
#100	258	8.7	13.5	10-20%
#200	204	6.9	6.6	7-15%
Pan	196	6.6	0.0	
<b>TOTAL</b>	2970			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	186	6.3	93.6	80-100%
#8	782	26.3	67.3	55-90%
#16	524	17.6	49.7	40-60%
#30	444	14.9	34.8	25-55%
#50	376	12.6	22.2	15-35%
#100	258	8.7	13.5	10-20%
#200	204	6.9	6.6	5-15%
Pan	196	6.6	0.0	
<b>TOTAL</b>	2970			