



RECYCLED COPPER SLAG
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	132	6.9	93.1	80-100%
#8	384	20.0	73.1	65-90%
#16	386	20.1	53.0	40-60%
#30	344	17.9	35.1	25-55%
#50	232	12.1	23.0	15-35%
#100	164	8.5	14.5	10-20%
#200	118	6.1	8.4	7-15%
Pan	162	8.4	0.0	
TOTAL	1922			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	132	6.9	93.1	80-100%
#8	384	20.0	73.1	55-90%
#16	386	20.1	53.0	40-60%
#30	344	17.9	35.1	25-55%
#50	232	12.1	23.0	15-35%
#100	164	8.5	14.5	10-20%
#200	118	6.1	8.4	5-15%
Pan	162	8.4	0.0	
TOTAL	1922			