



RED CEDAR GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	136	7.9	92.0	80-100%
#8	412	24.1	67.9	65-90%
#16	322	18.8	49.1	40-60%
#30	232	13.5	35.6	25-55%
#50	194	11.3	24.3	15-35%
#100	140	8.2	16.1	10-20%
#200	88	5.1	11.0	7-15%
Pan	188	11.0	0.0	
TOTAL	1712			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	136	7.9	92.0	80-100%
#8	412	24.1	67.9	55-90%
#16	322	18.8	49.1	40-60%
#30	232	13.5	35.6	25-55%
#50	194	11.3	24.3	15-35%
#100	140	8.2	16.1	10-20%
#200	88	5.1	11.0	5-15%
Pan	188	11.0	0.0	
TOTAL	1712			