



SALT & PEPPER GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	80	7.6	92.3	80-100%
#8	168	15.9	76.4	65-90%
#16	190	17.9	58.5	40-60%
#30	172	16.2	42.3	25-55%
#50	144	13.6	28.7	15-35%
#100	108	10.2	18.5	10-20%
#200	64	6.0	12.5	7-15%
Pan	132	12.5	0.0	
TOTAL	1058			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	80	7.6	92.3	80-100%
#8	168	15.9	76.4	55-90%
#16	190	17.9	58.5	40-60%
#30	172	16.2	42.3	25-55%
#50	144	13.6	28.7	15-35%
#100	108	10.2	18.5	10-20%
#200	64	6.0	12.5	5-15%
Pan	132	12.5	0.0	
TOTAL	1058			