



**SIERRA BLACK GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	9.4	89.6	80-100%
#8	110	10.4	79.2	65-90%
#16	242	22.8	56.4	40-60%
#30	200	18.9	37.5	25-55%
#50	172	16.2	21.3	15-35%
#100	104	9.8	11.5	10-20%
#200	34	3.2	8.3	7-15%
Pan	88	8.3	0.0	
<b>TOTAL</b>	1060			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	9.4	89.6	80-100%
#8	110	10.4	79.2	55-90%
#16	242	22.8	56.4	40-60%
#30	200	18.9	37.5	25-55%
#50	172	16.2	21.3	15-35%
#100	104	9.8	11.5	10-20%
#200	34	3.2	8.3	5-15%
Pan	88	8.3	0.0	
<b>TOTAL</b>	1060			