



**SNOW WHITE GRANITE**  
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	7.6	92.4	80-100%
#8	240	18.2	74.2	65-90%
#16	226	17.2	57.0	40-60%
#30	210	16.0	41.0	25-55%
#50	198	15.0	26.0	15-35%
#100	160	12.2	13.8	10-20%
#200	98	7.4	6.4	7-15%
Pan	84	6.4	0.0	
<b>TOTAL</b>	1316			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	100	7.6	92.4	80-100%
#8	240	18.2	74.2	55-90%
#16	226	17.2	57.0	40-60%
#30	210	16.0	41.0	25-55%
#50	198	15.0	26.0	15-35%
#100	160	12.2	13.8	10-20%
#200	98	7.4	6.4	5-15%
Pan	84	6.4	0.0	
<b>TOTAL</b>	1316			