



STARLIGHT BLACK GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	46	3.6	96.3	80-100%
#8	328	25.9	70.4	65-90%
#16	246	19.5	50.9	40-60%
#30	182	14.4	36.5	25-55%
#50	150	11.9	24.6	15-35%
#100	122	9.6	15.0	10-20%
#200	76	6.0	9.0	7-15%
Pan	114	9.0	0.0	
TOTAL	1264			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	46	3.6	96.3	80-100%
#8	328	25.9	70.4	55-90%
#16	246	19.5	50.9	40-60%
#30	182	14.4	36.5	25-55%
#50	150	11.9	24.6	15-35%
#100	122	9.6	15.0	10-20%
#200	76	6.0	9.0	5-15%
Pan	114	9.0	0.0	
TOTAL	1264			