



SUGAR & SPICE GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	414	30	69.9	65-90%
#16	288	20.9	49.0	40-60%
#30	182	13.2	35.8	25-55%
#50	160	11.6	24.2	15-35%
#100	120	8.7	15.5	10-20%
#200	84	6.1	9.4	7-15%
Pan	130	9.4	0.0	
TOTAL	1378			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	0	0.0	100	80-100%
#8	414	30	69.9	55-90%
#16	288	20.9	49.0	40-60%
#30	182	13.2	35.8	25-55%
#50	160	11.6	24.2	15-35%
#100	120	8.7	15.5	10-20%
#200	84	6.1	9.4	5-15%
Pan	130	9.4	0.0	
TOTAL	1378			