



SUNSET PINK GRANITE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	194	9.2	90.7	80-100%
#8	486	23.2	67.5	65-90%
#16	334	15.9	51.6	40-60%
#30	246	11.9	39.9	25-55%
#50	232	11.1	28.8	15-35%
#100	224	10.7	18.1	10-20%
#200	184	8.8	9.3	7-15%
Pan	196	9.3	0.0	
TOTAL	2096			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	194	9.2	90.7	80-100%
#8	486	23.2	67.5	55-90%
#16	334	15.9	51.6	40-60%
#30	246	11.9	39.9	25-55%
#50	232	11.1	28.8	15-35%
#100	224	10.7	18.1	10-20%
#200	184	8.8	9.3	5-15%
Pan	196	9.3	0.0	
TOTAL	2096			