



TURQUOISE MARBLE
PATHWAY SIEVE ANALYSIS



STANDARD PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	172	8.6	90.7	80-100%
#8	464	23.2	67.5	65-90%
#16	376	18.8	51.6	40-60%
#30	262	13.1	39.9	25-55%
#50	192	9.6	28.8	15-35%
#100	158	7.9	18.1	10-20%
#200	162	8.1	9.3	7-15%
Pan	214	10.7	0.0	
TOTAL	2000			

STABILIZED PATHWAY SIEVE ANALYSIS				
SIEVE	GRAMS	% RETAINED	% PASSING	SPEC PASSING
3/8"	0	0.0	100	100%
#4	172	8.6	91.4	80-100%
#8	464	23.2	68.2	55-90%
#16	376	18.8	49.4	40-60%
#30	262	13.1	36.3	25-55%
#50	192	9.6	26.7	15-35%
#100	158	7.9	18.8	10-20%
#200	162	8.1	10.7	5-15%
Pan	214	10.7	0.0	
TOTAL	2000			